## Polyethylene Treated Powders

## **Polyethylene Treated Powders**

Polyethylene을 처리한 파우더이며, 친유성 표면 특성으로 인해 오일에서 좋은 분산성을 제공합니다. oil cakes와 다른 oil 분산 타입제품에 적용할 수 있습니다.

Product name	INCI NAME	CAS No.	Average Primary Particle Size (#m)	Characterisitics
PLASTIC POWDER AP-18K	Polym ethyl Methacrylate, Polyethylene	9011-14- 79002-88-4	5~20	Powder with lipophilic surface properties. Improved dispersability. For oil cakes and other oil dispersion type porducts. Provides good spredability and elegant feel.
TiO2 AP- 12K	Titanium Dioxide, Polyehtylene	13463-67- 79002-88-4	0.2~0.4	Powder with lipophilic surface properties, Improved dispersability. For oil cakes and other oil dispersion type porducts. Provides good spredability and elegant feel.
Talc LP- 12K	Talc,Polyehtylene	14807-96- 69002-88-4	7~10	Powder with lipophilic surface properties, Improved dispersability. For oil cakes and other oil dispersion type porducts. Can be used as basic functional powder in the perparation
Black NP- 18K	Black Iron Oxide, Polyehtylene	1309-38- 29002-88-4	0.2~0.6	Powder with lipophilic surface properties, Improved dispersability. For oil cakes and other oil dispersion type porducts. Can be used as basic functional powder in the perparation
Red AFP- 18K	Iron Oxides, Polyehtylene	1309-37- 19002-88-4	0.05~0.4	Powder with lipophilic surface properties, Improved dispersability. For oil cakes and other oil dispersion type porducts. Can be used as basic functional powder in the perparation
Yellow RP- 18K	Iron Oxides, Polyehtylene	51274-00- 19002-88-4	0.05~0.4	Powder with lipophilic surface properties. Improved dispersability.For oil cakes and other oil dispersion type porducts. Can be used as basic functional powder in the perparation
Nylon Powder AP-18K	N ylon-12, Polyehtylene	25038-74- 89002-88-4	8~12	Powder with lipophilic surface properties. Improved dispersability.For oil cakes and other oil dispersion type porducts. Provides good spredability and elegant feel.
Mica HP- 18K	Mica, Polyehtylene	12001-26- 29002-88-4	24~28	Powder with lipophilic surface properties. Improved dispersability.For oil cakes and other oil dispersion type porducts. Can be used as basic functional powder in the preparation.